## Technical Data Sheet

Columbia Coatings 1173 Industrial Park Rd Columbia, TN 38401 931-388-7730 931-388-5573 FAX



Number:	S5174050
Name:	Baby Blue
Type:	TGIC

## **Powder Properties**

Specific Gravity	Approx. 1.66 g/cm <sup>3</sup>
Storage Temp	< 77°F (25°C)
Theoretical Coverage	116 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

## **Coating Properties**

Film Thickness	Recommended Film Thickness: 2–3 mils
Cure Schedule	Metal Temperature: 10 minutes at 340°F (171°C)
Gloss Level	90+% @ 60°
Pencil Hardness	2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	5B (ASTM D3359)
Direct Impact	160 in-lb. direct (ASTM D2794)
Reverse Impact	160 in-lb. direct (ASTM D2794)
Salt Spray	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117)

www.columbiacoatings.com