

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	B5786001
Name:	Basic Red
Type:	TGIC

Powder Properties

Specific Gravity	1.23 +/- .05
Storage Temp	80°F (27°C) up to 1 year
Theoretical Coverage	63 sq./ft @ 2.5 mils
Particle Distribution	+44 MICRONS (325 MESH) 35 - 45%

Coating Properties

Film Thickness	Recommended film thickness 2-3 mils
Cure Schedule	Metal Temperature: 10 minutes @ 400°F (204°C)
Gloss Level	80-85%
Pencil Hardness	ASTM D3363 H-2H
Flexibility	1/8" ASTM D522
Adhesion	5B
Direct Impact	160 in-lb. direct;
Reverse Impact	160 in-lb. reverse (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com