

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	IM1500032
Name:	Can-Am Texture Black
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.73 g/cm ³
Storage Temp	< 80°F (27°C)
Theoretical Coverage	111 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2–4 mils
Cure Schedule	Metal Temperature: 10 minutes at 400°F (204°C)
Gloss Level	5-10% @ 60°
Pencil Hardness	H-2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	5B (ASTM D3359)
Direct Impact	80 in-lb. direct (ASTM D2794)
Reverse Impact	80 in-lb. direct (ASTM D2794)
Salt Spray	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117)

www.columbiacoatings.com