

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	CS8695066
Name:	Mystique
Type:	Acrylic

Powder Properties

Specific Gravity	1.16 (\pm 0.05) g/cm ³
Storage Temp	< 70°F (21°C)
Theoretical Coverage	166 ft ² /lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2 - 4 mils
Cure Schedule	Metal Temperature: 17 minutes @ 350°F (177°C)
Gloss Level	90+% @ 60°
Pencil Hardness	H – 2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	100% (ASTM D3359)
Direct Impact	20 in/lb. (ASTM D2794)
Reverse Impact	20 in/lb. (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com