Technical Data Sheet

Columbia Coatings 1173 Industrial Park Rd Columbia, TN 38401 931-388-7730 931-388-5573 FAX



Number:	S1700091
Name:	Soft White
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.68 g/cm ³
Storage Temp	< 77°F (25°C)
Theoretical Coverage	115 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2–3 mils
Cure Schedule	Metal Temperature: 10 minutes at 400°F (204°C)
Gloss Level	0-10% @ 60°
Pencil Hardness	H-2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	5B (ASTM D3359)
Direct Impact	160 in-lb. direct (ASTM D2794)
Reverse Impact	160 in-lb. direct (ASTM D2794)
Salt Spray	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117)
Humidity	1000 Hrs.

www.columbiacoatings.com