

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	T1796024G
<b>Name:</b>	Strawberry Fields
<b>Type:</b>	Translucent

## Powder Properties

<b>Specific Gravity</b>	1.2-1.8 g/cm <sup>3</sup>
<b>Storage Temp</b>	77°F (25°C)
<b>Theoretical Coverage</b>	51.5 ft <sup>2</sup> /lb.
<b>Particle Distribution</b>	n/a

## Coating Properties

<b>Film Thickness</b>	2-3 mils
<b>Cure Schedule</b>	Metal Temperature: 10 minutes @ 400°F (204°C)
<b>Gloss Level</b>	80-90%
<b>Pencil Hardness</b>	2H minimum
<b>Flexibility</b>	1/8" Mandrel
<b>Adhesion</b>	5B
<b>Direct Impact</b>	80 in/lb.
<b>Reverse Impact</b>	n/a
<b>Salt Spray</b>	1/32" @ 500 hrs.

[www.columbiacoatings.com](http://www.columbiacoatings.com)