## Columbia Coatings Technical Data Sheet

Columbia Coatings 1173 Industrial Park Rd Columbia, TN 38401 931-388-7730 931-388-5573 FAX



Number:	M1695065
Name:	Cotton Candy
Туре:	Polyester/TGIC

## **Powder Properties**

Specific Gravity	$1.20 \pm .05 \text{ g/cm}^3$
Storage Temp	Less than 80°F (27°C)
Theoretical Coverage	161 sq./ft @ 1 mil
Particle Distribution	n/a

## **Coating Properties**

Film Thickness	2.0 – 3.0 mils
Cure Schedule	Metal Temperature: 10 Minutes @ 400°F (204°C)
Gloss Level	90+% @ 60°
Pencil Hardness	(ASTM D3363) H-2H
Flexibility	n/a
Adhesion	(ASTM D3359) 100%
Direct Impact	(ASTM D2794) 140 in./lb.
Reverse Impact	(ASTM D2794) 140 in./lb.
Salt Spray	(ASTM B117) 2000 hrs.

## www.columbiacoatings.com