

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	Polaris Ghost White
Name:	IM1700034
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.68 g/cm ³
Storage Temp	< 80°F (27°C)
Theoretical Coverage	115 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended Film Thickness: 2 – 3 mils
Cure Schedule	Metal Temperature: 10 minutes at 400°F (204°C)
Gloss Level	0-10% @ 60°
Pencil Hardness	H - 2H (ASTM D3363)
Flexibility	3/8" (ASTM D522)
Adhesion	5B (ASTM D3359)
Direct Impact	160 in-lb. direct (ASTM D2794)
Reverse Impact	160 in-lb. reverse (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com