

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	I5706037
Name:	Matte Waukee Red
Type:	TGIC

Powder Properties

Specific Gravity	Approx. 1.20 g/cm ³
Storage Temp	< 77°F (25°C)
Theoretical Coverage	161 sq. ft/lb. @ 1 mil
Particle Distribution	35 – 55 micron averages

Coating Properties

Film Thickness	Recommended Film Thickness: 2–3 mils
Cure Schedule	Metal Temperature: 10 minutes at 400°F (204°C)
Gloss Level	0-10% @ 60°
Pencil Hardness	H-2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	100%
Direct Impact	20 in-lb. direct (ASTM D2794)
Reverse Impact	20 in-lb. direct (ASTM D2794)
Salt Spray	1000 Hrs. Pass <1/8" Scribe Creep - No Blisters (ASTM B117)

www.columbiacoatings.com